



## KÖSTER Joint Sealant FS-V black

Technical Data Sheet J 231

Issued: 2017-07-21

Official Test Certificate, OMTL, Hanover - resistance to diesel oil

### Stiff / creamy 2 component polysulphide joint sealant

	<p><b>KÖSTER BAUCHEMIE AG</b>          Dieselstraße 1-10, 26607 Aurich          17          J 231</p> <p><b>EN 14188-2 Black</b>  <b>KÖSTER Joint Sealant FS-V</b>  <b>Cold applied jointing material</b>  <b>for streets, bridge decks,</b>  <b>parking lots, etc.</b></p>
Adhesion and elongation capacity	Modulus of tension at 100% elongation at + 23 °C ≥ 0.15 MPA at - 20 °C ≤ 0.6 MPA
Adhesion capacity	no failure at - 20 °C ≤ 0.6 MPa
Water impermeability	Modulus of tension at 100% elongation at + 23 °C ≥ 0.15 MPA at - 20 °C ≤ 0.6 MPA No failure at -20 °C ≤ 0.6 MPa
Resistance to deflection	Resilience ≥ 70% Volume loss ≤ 5%
Durability of water impermeability under chemical attack	Passed
Durability of all mandated properties against aging	Change in modulus of tension at 100% elongation ≤ +/- 20%
Resistance to flames	Passed

#### Features

KÖSTER Joint Sealant FS-V is a flexible stiff / creamy polysulphide joint sealant. When fully cured, KÖSTER Joint Sealant FS-V is a rubbery elastic sealant with a high mechanical load capacity, good resistance to water, sea water, salt solutions, benzenes and mineral oils; it is root resistant, does not rot and it has very good retraction capabilities.

#### Technical Data

Colors	light grey, black
Mixing ratio by weight	100 : 13 (A : B)
Pot life	approx. 2 hours (+ 20 °C, 50 % rel. hum.)
Curing time	approx. 24 hours (+ 23 °C, 50 % rel. hum.)
Consistency	stiff / creamy
Specific gravity	approx. 1.6 kg/l
Shore A-hardness	approx. 35
Retraction capacity	≥ 80 %
Total deformation permitted	15 %
Application temperature	+ 5 °C to + 40 °C

#### Fields of Application

KÖSTER Joint Sealant FS-V can be used to permanently and elastically seal vertical joints in below grade construction, cracks in

basements, building foundations, joints in sewage treatment plants, garages, tunnels, etc. It is also suited for application on horizontal joints.

#### Substrate

The flanks of the joints have to be clean, solid, and free of grease and dust. Substrates must be primed with KÖSTER FS-Primer 2C.

#### Application

Mix both components thoroughly using a slow speed mixer until a homogeneous consistency is reached, (at least 3 minutes). The joint is filled approx. 2 hours after priming with a caulking gun, (smoothing) trowel, spatula or straight edge.  
Observe the DIN 18540.

#### Consumption

Approx. 1.6 kg/l void

Joint width in mm	10	15	20	25	30	35
Thickness of joint sealant (in mm)	8	10	12	15	18	20
Deviation allowed (in mm)	+/-2	+/-2	+/-2	+/-3	+/-3	+/-4
Distance of joints allowed in m	2-4	2-6	4-7	5-8	6-9	7-10
Consumption on kg / m	0,13	0,24	0,38	0,60	0,72	1.12

#### Cleaning

Clean tools immediately after use with KÖSTER Universal Cleaner.

#### Packaging

J 231 004 4 kg combipackage

#### Storage

Store the material dry and frost free. In originally sealed packages it can be stored for a minimum of 6 months.

#### Safety

Wear safety gloves and goggles when working with the material.

#### Related products

KÖSTER FS Primer 2C	Prod. code J 139 200
KÖSTER Joint Sealant FS-H black	Prod. code J 232
KÖSTER Joint Sealant FS-V grey	Prod. code J 233
KÖSTER Joint Sealant FS-H grey	Prod. code J 234
KÖSTER Universal Cleaner	Prod. code X 910 010

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

J - Joint sealing